



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C11D 17/00	A1	(11) International Publication Number: WO 99/55822 (43) International Publication Date: 4 November 1999 (04.11.99)
(21) International Application Number: PCT/IB99/00710 (22) International Filing Date: 21 April 1999 (21.04.99) (30) Priority Data: 60/083,264 27 April 1998 (27.04.98) US (71) Applicant (for all designated States except US): THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): ANGELL, Adrian, John, Waynforth [GB/US]; 6837 Hidden Ridge Drive, West Chester, OH 45069 (US). ZORB, Les, Charles [US/US]; 6674 Paxton Guinea Road, Loveland, OH 45140 (US). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).		(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR MAKING NON-PARTICULATE DETERGENT PRODUCT READILY DISPERSIBLE IN WATER (57) Abstract <p>A process for producing a water-dispersible non-particulate detergent product includes the step of providing a particulate detergent composition. The process further includes the step of adding a flow aid to the particulate detergent composition in a range of from about 0.1 % to about 25 % by weight of the particulate detergent composition. The process then includes the step of compacting the particulate detergent composition having the flow aid by applying a pressure in an amount sufficient to form the water-dispersible non-particulate detergent product having a density of at least about 1000 g/l. This process enables the manufacture of a rapidly dispersing non-particulate detergent composition that sinks in water.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PROCESS FOR MAKING NON-PARTICULATE DETERGENT PRODUCT
READILY DISPERSIBLE IN WATER

5

TECHNICAL FIELD

The present invention relates to detergent compositions in non-particulate form. More particularly, the invention relates to a process for improving the dispersibility of a non-particulate detergent composition, e.g., tablet, block or bar, in water, by enabling the manufacture of a non-particulate detergent product that sinks in water and rapidly disintegrates and dissolves in water

BACKGROUND OF THE INVENTION

Non-particulate detergents are an alternative to granular or particulate forms of detergents for simplifying the dosing of such detergents for automatic washing machines, such as laundry or dishwashing machines. Such non-particulate detergents are usually supplied in the form of bars, tablets or briquettes. Such non-particulate detergents not only prevent spillage of the detergent composition but also eliminate the need for the consumer to estimate the correct dosage of the detergent composition per wash. Further, such non-particulate detergents also minimize the contact by the consumer with the detergent.

An important factor for successful performance of a non-particulate detergent is its ability to dissolve in the washing machine in a controlled manner according to a desired dissolution profile during the program cycle of the machine. Another important performance factor is that the non-particulate detergent should be hard enough to facilitate easy handling of the detergent prior to use, so that it does not inadvertently lose its structure, crumble, or deteriorate, both during the packaging, transport and storage and during handling by the end consumer prior to actual use. Such performance aspects are an important feature of the non-particulate detergent, and although they are not necessarily the focus of the present invention, they are inherently a part of the background of the present invention.

Additionally, a very desirable feature of a non-particulate detergent, such as for example, a tablet, is its ability to sink in water and rapidly disperse in water to form a wash solution. In order to sink in water, a detergent tablet must have a density greater than 1000 g/l and in order to disperse in water, a detergent tablet
35 must be able to break up in water. However, when laundry tablets are made from low bulk density detergents, such as those made by spray dried processes, wherein the detergent powder has a bulk density less than about 650 g/l, the problem frequently encountered is that the force required to compact the detergent powder into tablets having a density of at least 1000 g/l is so high that the detergent tablets
40 do not readily disperse in water. This problem is further escalated by the fact that detergent powders made from spray dried processes tend to be more porous and sticky. Thus when these detergent powders are pressed into tablets having a density of at least 1000 g/l, the powder particles stick together and consequently the tablet does not readily break up and dissolve in water. Conversely, if the tablets made
45 from low bulk density detergent powders are compacted using a lower force, they generally disperse in water but at a slower rate because they have a density less than 1000 g/l and thus tend to float in water before fully dispersing in water.

The above problem is usually not encountered when making detergent tablets from a detergent powder made by agglomeration processes because detergent
50 powders made by agglomeration processes usually have a bulk density in a range of about 700 g/l to about 850 g/l and consequently, the force required to compress the powder into a tablet having a density of at least 1000 g/l is not so high. Thus detergent tablets made by compacting detergent powders made from agglomeration process usually sink in water. However, agglomeration process detergents or
55 "agglomerates", which inherently have higher density than spray dried process detergents or "spray dried granules", generally exhibit slower dissolution rates in water, as compared to spray dried granules.

Thus the production of detergent tablets is a complex matter. It involves more than the mere selection of components or the compression of a particular
60 detergent composition into a tablet. The tablet must be capable of withstanding the shocks of packaging, handling and distribution without crumbling. In other words

the tablet must be strong. But the tablet must also have a satisfactory rate of disintegration when immersed in water. The tablets known so far have generally shown too long a disintegration time, in favor of their strength, or they have had a
65 very low strength, in favor of their shorter disintegration time.

It is highly desirable to have a laundry detergent tablet with a core which is formed by compressing a particulate material which has a deterative surfactant and a builder and wherein the particulate material is processed in a manner so as to make the individual particles sticky enough to stay together when the material is
70 compressed into a tablet form, yet not too sticky to not disintegrate rapidly when immersed in water. This becomes a very challenging problem in light of the additional desirable requirement that the detergent tablet, after compaction, have a density of at least 1000 g/l so that it sinks in water.

This kind of a tablet performance has heretofore not been available and this
75 level of performance requires not only careful selection of the type of detergent that makes up the core, but also requires novel ways to surface treat the detergent particles prior to compaction so as have just the right amount of stickiness. The present invention overcomes the problems as outlined above.

BACKGROUND ART

80 The prior art is replete with methods of forming tablets and coating tablets.

One approach has been to use acetate salt to improve the dissolution rate of detergents compressed in the form of tablets. EP-A-0002293, published on 13th June 1979, discloses detergent tablets containing hydrated salt. The preferred hydrate salt is a mixture of sodium acetate trihydrate and sodium metaborate tetrahydrate.

85 Another approach known in the art is to use effervescent aids to improve tablet disintegration. CA-A-2040307 discloses laundry detergent tablets comprising anionic surfactants mixed with sodium carbonate and citric acid.

As far as coated tablets are concerned, GB-A-0 989 683, published on 22nd April 1965, discloses a process for preparing a particulate detergent from surfactants
90 and inorganic salts; spraying on water-soluble silicate; and pressing the detergent particles into a solid form-retaining tablet. Finally a readily water-soluble organic

film-forming polymer (for example, polyvinyl alcohol) provides a coating to make the detergent tablet resistant to abrasion and accidental breakage.

European publication, EP-A-0 002 293, published on 13th June 1979,
95 discloses a tablet coating comprising hydrated salt such as acetate, metaborate, orthophosphate, tartrate, and sulphate. Another European publication, EP-A-0 716 144, published on 12th June 1996, also discloses laundry detergent tablets with water-soluble coatings which may be organic polymers including acrylic/maleic copolymer, polyethylene glycol, PVPVA, and sugar.

100 SUMMARY OF THE INVENTION

The invention meets the needs above by providing a process for producing a water-dispersible non-particulate detergent product. Specifically, in one aspect of the present invention, the process comprises the step of providing a particulate detergent composition. The process further includes the step of adding a flow aid to
105 the particulate detergent composition in a range of from about 0.1% to about 25% by weight of the particulate detergent composition. The process then includes the step of compacting the particulate detergent composition having the flow aid by applying a pressure in an amount sufficient to form the water-dispersible non-particulate detergent product having a density of at least about 1000 g/l.

110 In another aspect of the present invention, a method of laundering fabric materials in a washing machine is provided. The method includes the steps of providing a flexible porous bag adapted for receiving a non-particulate detergent product, providing a non-particulate detergent product, placing the non-particulate detergent product within the flexible porous bag, and placing the flexible porous bag
115 containing the detergent product in the washing machine with the fabric materials to be washed. The flexible porous bag is adapted for permitting entry of an aqueous washing medium through the bag, thereby dissolving the non-particulate detergent product placed therein, into the aqueous washing medium, and releasing a resultant wash solution from inside of the bag to outside of the bag and into the aqueous wash
120 medium during a wash cycle.

In yet another aspect of the present invention, a method of laundering soiled clothes includes the step of immersing the soiled clothes in an aqueous medium

containing an effective amount of a non-particulate detergent product made by a process which includes the steps of providing a particulate detergent composition, adding a flow aid to the particulate detergent composition in a range of from about 0.1% to about 25% by weight of the particulate detergent composition and compacting the particulate detergent composition having the flow aid by applying a pressure in an amount sufficient to form the water-dispersible non-particulate detergent product having a density of at least about 1000 g/l.

In yet another aspect of the present invention, a water-dispersible non-particulate detergent product is disclosed. The product includes a core formed by compacting a particulate detergent composition to a density of at least about 1000 g/l. The particulate detergent composition has a bulk density in a range of from about 600 g/l to about 850 g/l. The particulate detergent composition comprises a flow aid in a range of from about 0.1% to about 25% by weight of the particulate detergent composition.

DETAILED DESCRIPTION OF THE INVENTION

Process

In the preferred embodiment of the present invention, the process includes the step of providing a particulate detergent composition.

The particulate detergent composition

The term "particulate" as used herein means forms such as powders, granules, particles, flakes and other similar particulate forms that are capable of being compacted into a more dense non-particulate form.

145 In particular for laundry tablets, detergent particles having ingredients such as builder and surfactant can be spray-dried in a conventional manner and then compacted at a suitable pressure. The surfactants and builders normally provide a substantial part of the cleaning power of the tablet. The term "builder" is intended to mean all materials which tend to remove calcium ion from solution, either by ion
150 exchange, complexation, sequestration or precipitation.

The particulate material used for making the detergent tablet provided in this invention can be made by any particulation or granulation process. An example of such a process is spray drying (in a co-current or counter current spray drying tower) which typically gives "spray-dried" detergent granules having low bulk densities of
155 600g/l or lower. Particulate materials of higher density can be prepared by granulation and densification in a high shear batch mixer/granulator or by a continuous granulation and densification process (e.g. using Lodige® CB and/or Lodige® KM mixers). Other suitable processes include fluid bed processes, compaction processes (e.g. roll compaction), extrusion, as well as any particulate
160 material made by any chemical process like flocculation, crystallization sentering, etc. The individual particles can also be in any other form, such as for example, particle, granule, sphere or grain.

The particulate materials may be mixed together by any conventional means, for example, a concrete mixer, Nauta mixer, ribbon mixer or any other.
165 Alternatively the mixing process may be carried out continuously by metering each component by weight on to a moving belt, and blending them in one or more drum(s) or mixer(s). A liquid spray-on to the mix of particulate materials (e.g. non-ionic surfactants) may be carried out. Other liquid ingredients may also be sprayed on to the mix of particulate materials either separately or premixed. For example
170 perfume and slurries of optical brighteners may be sprayed. A finely divided flow aid (dusting agent such as zeolites, carbonates, silicas) can be added to the

particulate materials after spraying the non-ionic, preferably towards the end of the process, to make the mix less sticky.

The detergent particles can be made by an agglomerate process comprising
175 the steps of:

- i) admixing one or more detergent surfactants, a perborate component and an acid source and optionally other detergent ingredients to form a mixture; and
- ii) agglomerating the mixture to form agglomerated particles or "agglomerates".

180 Typically, such an agglomeration process involves mixing an effective amount of powder, including the acid source, with a high active surfactant paste in one or more agglomerators such as a pan agglomerator, a Z-blade mixer or more preferably in-line mixers, preferably two, such as those manufactured by Schugi (Holland) BV, 29 Chroomstraat 8211 AS, Lelystad, Netherlands, and Gebruder
185 Lodige Maschinenbau GmbH, D-4790 Paderborn 1, Elsenerstrasse 7-9, Postfach 2050, Germany. Preferably a high shear mixer is used, such as a Lodige CB (Trade Name). Most preferably, a high shear mixer is used in combination with a low shear mixer, such as a Lodige CB (Trade Name) and a Lodige KM (Trade name) or Schugi KM (Trade Name). Optionally, only one or more low shear mixer are used.
190 Preferably, the agglomerates are thereafter dried and/ or cooled.

Another agglomeration process involves mixing of various components of the final agglomerate in different stages, using an fluidized bed. For example, a preferred particulate detergent in accordance with the present invention can be agglomerated by addition, preferably by spraying on, of nonionic, anionic
195 surfactants and optionally a wax, or mixtures thereof, to the acid source in powdered form and other optional ingredients. Then, additional components, including the perborate bleach and optionally the alkali source or part thereof, can be added and agglomerated in one or more stages, thus forming the final agglomerate particle.

The agglomerates may take the form of flakes, prills, marumes, noodles,
200 ribbons, but preferably take the form of granules. A preferred way to process the particles is by agglomerating powders (e.g. aluminosilicate, carbonate) with high active surfactant pastes and to control the particle size of the resulting agglomerates within specified limits. Typical particle sizes are from 0.10 mm to 5.0 mm in diameter, preferably from 0.25 mm to 3.0 mm in diameter, most preferably from

205 0.40 mm to 1.00 mm in diameter. Typically, the "agglomerates" have a bulk density desirably, of at least 700 g/l and preferably, in a range of from about 700 g/l to about 900 g/l.

A high active surfactant paste comprising a mix of, typically, from 50% by weight to 95% by weight, preferably 70% by weight to 85% by weight of surfactant, 210 and optionally it can contain an appropriate acid source. The paste may be pumped into the agglomerator at a temperature high enough to maintain a pumpable viscosity, but low enough to avoid degradation of the anionic surfactants used. An operating temperature of the paste of 50°C to 80°C is typical. Such pastes and methods for making and processing such pastes is for example described in WO 215 93/03128. In an especially preferred embodiment of the present invention, the detergent particles made by agglomeration process have a bulk density of greater than about 600 g/l and the detergent is in the form of powder or a granulate.

In the preferred embodiment of the present invention, the particulate detergent composition is a mixture of spray dried process and agglomeration process 220 detergents, such that the final bulk density of the detergent composition is in a range of desirably, no greater than about 900 g/l, more desirably, in a range of from about 600 g/l to about 850 g/l, and preferably, in a range of from about 625 g/l to about 725 g/l. These ranges of bulk density are desirable because if the bulk density of the particulate detergent from which the tablet is to be compressed is greater than about 225 900 g/l, then the solubility of the detergent tablet will be detrimentally affected. A bulk density less than about 600 g/l is undesirable because at values less than about 600 g/l, the amount of pressure required to form a detergent tablet having a density of at least 1000 g/l is so high that the tablet will not break up easily in water and will not dissolve rapidly.

230 To achieve the desired bulk densities as set forth above, the particulate detergent composition contains selected amounts of spray dried granules and detergent agglomerates in an optimum proportion. In this regard, the composition comprises desirably from about 40% to about 80%, preferably from about 40% to about 60%, and more preferably from about 45% to about 55%, by weight, of spray 235 dried. Desirably, the composition includes from about 20% to about 60%,

preferably from about 40% to about 60%, and more preferably from about 45% to about 55%, by weight, of agglomerates.

Dry Detergent Material


The starting dry detergent material of the present process preferably comprises
240 materials selected from the group consisting of carbonates, sulfates, carbonate/sulfate
complexes, tripolyphosphates, tetrasodium pyrophosphate, citrates, aluminosilicates,
cellulose-based materials and organic synthetic polymeric absorbent gelling materials.
More preferably, the dry detergent material is selected from the group consisting of
aluminosilicates, carbonates, sulfates, carbonate/sulfate complexes, and mixtures
245 thereof. Most preferably, the dry detergent material comprise a detergent
aluminosilicate builder which are referenced as aluminosilicate ion exchange materials
and sodium carbonate.

The aluminosilicate ion exchange materials used herein as a detergent builder
preferably have both a high calcium ion exchange capacity and a high exchange rate.
250 Without intending to be limited by theory, it is believed that such high calcium ion
exchange rate and capacity are a function of several interrelated factors which derive
from the method by which the aluminosilicate ion exchange material is produced. In
that regard, the aluminosilicate ion exchange materials used herein are preferably
produced in accordance with Corkill et al, U.S. Patent No. 4,605,509 (Procter &
255 Gamble), the disclosure of which is incorporated herein by reference.


Preferably, the aluminosilicate ion exchange material is in "sodium" form since
the potassium and hydrogen forms of the instant aluminosilicate do not exhibit the as
high of an exchange rate and capacity as provided by the sodium form. Additionally,
the aluminosilicate ion exchange material preferably is in over dried form so as to
260 facilitate production of crisp detergent agglomerates as described herein. The
aluminosilicate ion exchange materials used herein preferably have particle size
diameters which optimize their effectiveness as detergent builders. The term "particle
size diameter" as used herein represents the average particle size diameter of a given
aluminosilicate ion exchange material as determined by conventional analytical
265 techniques, such as microscopic determination and scanning electron microscope
(SEM). The preferred particle size diameter of the aluminosilicate is from about 0.1

micron to about 10 microns, more preferably from about 0.5 microns to about 9 microns. Most preferably, the particle size diameter is from about 1 microns to about 8 microns.

270 Preferably, the aluminosilicate ion exchange material has the formula



wherein z and y are integers of at least 6, the molar ratio of z to y is from about 1 to about 5 and x is from about 10 to about 264. More preferably, the aluminosilicate has the formula



wherein x is from about 20 to about 30, preferably about 27. These preferred aluminosilicates are available commercially, for example under designations Zeolite A, Zeolite B and Zeolite X. Alternatively, naturally-occurring or synthetically derived aluminosilicate ion exchange materials suitable for use herein can be made as described in Krummel et al, U.S. Patent No. 3,985,669, the disclosure of which is incorporated herein by reference.

280 The aluminosilicates used herein are further characterized by their ion exchange capacity which is at least about 200 mg equivalent of CaCO_3 hardness/gram, calculated on an anhydrous basis, and which is preferably in a range from about 300 to 352 mg equivalent of CaCO_3 hardness/gram. Additionally, the instant aluminosilicate ion exchange materials are still further characterized by their calcium ion exchange rate which is at least about 2 grains Ca^{++} /gallon/minute/-gram/gallon, and more preferably in a range from about 2 grains Ca^{++} /gallon/minute/-gram/gallon to about 6 grains Ca^{++} /gallon/minute/-gram/gallon.

290 Additionally, those builder materials discussed previously as an optional coating agent can be used herein. These particular builder materials have the formula $(\text{M}_x)_i \text{Ca}_y (\text{CO}_3)_z$ wherein x and i are integers from 1 to 15, y is an integer from 1 to 10, z is an integer from 2 to 25, M_i are cations, at least one of which is a water-soluble, and the equation $\sum_i = 1-15(x_i \text{ multiplied by the valence of } \text{M}_i) + 2y = 2z$ is satisfied such that the formula has a neutral or "balanced" charge. Additional details and examples of these builder materials have been set forth previously and are incorporated herein by

reference. Preferably, these builder materials are selected from the group consisting of $\text{Na}_2\text{Ca}(\text{CO}_3)_2$, $\text{K}_2\text{Ca}(\text{CO}_3)_2$, $\text{Na}_2\text{Ca}_2(\text{CO}_3)_3$, $\text{NaKCa}(\text{CO}_3)_2$, $\text{NaKCa}_2(\text{CO}_3)_3$, $\text{K}_2\text{Ca}_2(\text{CO}_3)_3$, and combinations thereof.

300

Adjunct Detergent Ingredients


The starting dry detergent material in the present process can include additional detergent ingredients and/or, any number of additional ingredients can be incorporated in the detergent composition during subsequent steps of the present process. These adjunct ingredients include other detergency builders, bleaches, bleach activators, suds
305 boosters or suds-suppressers, anti-tarnish and anticorrosion agents, soil suspending agents, soil release agents, germicides, pH adjusting agents, non-builder alkalinity sources, chelating agents, smectite clays, enzymes, enzyme-stabilizing agents and perfumes. See U.S. Patent 3,936,537, issued February 3, 1976 to Baskerville, Jr. et al., incorporated herein by reference.

310


Other builders can be generally selected from the various water-soluble, alkali metal, ammonium or substituted ammonium phosphates, polyphosphates, phosphonates, polyphosphonates, carbonates, borates, polyhydroxy sulfonates, polyacetates, carboxylates, and polycarboxylates. Preferred are the alkali metal, especially sodium, salts of the above. Preferred for use herein are the phosphates,
315 carbonates, C_{10-18} fatty acids, polycarboxylates, and mixtures thereof. More preferred are sodium tripolyphosphate, tetrasodium pyrophosphate, citrate, tartrate mono- and di-succinates, and mixtures thereof (see below).

In comparison with amorphous sodium silicates, crystalline layered sodium silicates exhibit a clearly increased calcium and magnesium ion exchange capacity. In
320 addition, the layered sodium silicates prefer magnesium ions over calcium ions, a feature necessary to insure that substantially all of the "hardness" is removed from the wash water. These crystalline layered sodium silicates, however, are generally more expensive than amorphous silicates as well as other builders. Accordingly, in order to provide an economically feasible laundry detergent, the proportion of crystalline
325 layered sodium silicates used must be determined judiciously.

The crystalline layered sodium silicates suitable for use herein preferably have the formula



wherein M is sodium or hydrogen, x is from about 1.9 to about 4 and y is from about 0
330 to about 20. More preferably, the crystalline layered sodium silicate has the formula



wherein M is sodium or hydrogen, and y is from about 0 to about 20. These and other
crystalline layered sodium silicates are discussed in Corkill et al, U.S. Patent No.
4,605,509, previously incorporated herein by reference.

335 Specific examples of inorganic phosphate builders are sodium and potassium
tripolyphosphate, pyrophosphate, polymeric metaphosphate having a degree of
polymerization of from about 6 to 21, and orthophosphates. Examples of
polyphosphonate builders are the sodium and potassium salts of ethylene
diphosphonic acid, the sodium and potassium salts of ethane 1-hydroxy-1,
340 1-diphosphonic acid and the sodium and potassium salts of ethane,
1,1,2-triphosphonic acid. Other phosphorus builder compounds are disclosed in
U.S. Patents 3,159,581; 3,213,030; 3,422,021; 3,422,137; 3,400,176 and 3,400,148,
all of which are incorporated herein by reference.

Examples of nonphosphorus, inorganic builders are tetraborate decahydrate
345 and silicates having a weight ratio of SiO_2 to alkali metal oxide of from about 0.5 to
about 4.0, preferably from about 1.0 to about 2.4. Water-soluble, nonphosphorus
organic builders useful herein include the various alkali metal, ammonium and
substituted ammonium polyacetates, carboxylates, polycarboxylates and
polyhydroxy sulfonates. Examples of polyacetate and polycarboxylate builders are
350 the sodium, potassium, lithium, ammonium and substituted ammonium salts of
ethylene diamine tetraacetic acid, nitrilotriacetic acid, oxydisuccinic acid, mellitic
acid, benzene polycarboxylic acids, and citric acid.

Polymeric polycarboxylate builders are set forth in U.S. Patent 3,308,067,
Diehl, issued March 7, 1967, the disclosure of which is incorporated herein by
355 reference. Such materials include the water-soluble salts of homo- and copolymers
of aliphatic carboxylic acids such as maleic acid, itaconic acid, mesaconic acid,
fumaric acid, aconitic acid, citraconic acid and methylene malonic acid. Some of

these materials are useful as the water-soluble anionic polymer as hereinafter described, but only if in intimate admixture with the non-soap anionic surfactant.

360 Other suitable polycarboxylates for use herein are the polyacetal carboxylates described in U.S. Patent 4,144,226, issued March 13, 1979 to Crutchfield et al, and U.S. Patent 4,246,495, issued March 27, 1979 to Crutchfield et al, both of which are incorporated herein by reference. These polyacetal carboxylates can be prepared by bringing together under polymerization conditions an ester of glyoxylic acid and a
365 polymerization initiator. The resulting polyacetal carboxylate ester is then attached to chemically stable end groups to stabilize the polyacetal carboxylate against rapid depolymerization in alkaline solution, converted to the corresponding salt, and added to a detergent composition. Particularly preferred polycarboxylate builders are the ether carboxylate builder compositions comprising a combination of tartrate
370 monosuccinate and tartrate disuccinate described in U.S. Patent 4,663,071, Bush et al., issued May 5, 1987, the disclosure of which is incorporated herein by reference.

 Bleaching agents and activators are described in U.S. Patent 4,412,934, Chung et al., issued November 1, 1983, and in U.S. Patent 4,483,781, Hartman, issued November 20, 1984, both of which are incorporated herein by reference. Chelating
375 agents are also described in U.S. Patent 4,663,071, Bush et al., from Column 17, line 54 through Column 18, line 68, incorporated herein by reference. Suds modifiers are also optional ingredients and are described in U.S. Patents 3,933,672, issued January 20, 1976 to Bartoletta et al., and 4,136,045, issued January 23, 1979 to Gault et al., both incorporated herein by reference.

380 Suitable smectite clays for use herein are described in U.S. Patent 4,762,645, Tucker et al, issued August 9, 1988, Column 6, line 3 through Column 7, line 24, incorporated herein by reference. Suitable additional detergency builders for use herein are enumerated in the Baskerville patent, Column 13, line 54 through Column 16, line 16, and in U.S. Patent 4,663,071, Bush et al, issued May 5, 1987, both incorporated
385 herein by reference.

The non-particulate detergent product

The detergent tablets can be prepared simply by mixing the solid ingredients together and compressing the mixture in a conventional tablet press as used, for example, in the pharmaceutical industry.

390 The detergent tablets provided can be made in any size or shape and are desirably surface treated with a flow aid according to the present invention. The detergent tablets provided may be manufactured by using any compacting process, such as tableting, briquetting, or extrusion, preferably tableting. Suitable equipment includes a standard single stroke or a rotary press (such as Courtoy®, 395 Korch®, Manesty®, or Bonals®). As used herein, the term "non-particulate detergent product" includes physical shapes such as tablets, blocks, bars and the like.

Coating for non-particulate detergent product

In one embodiment, the tablets are coated with a coating in order to provide mechanical strength and shock and chip resistance to the compressed tablet core. 400 The tablets are coated with a coating that is substantially insoluble in water so that the tablet does not absorb moisture, or absorbs moisture at only a very slow rate. The coating is strong so that moderate mechanical shocks to which the tablets are subjected during handling, packing and shipping result in no more than very low levels of breakage or attrition. Further, the coating is preferably brittle so that the 405 tablet breaks up when subjected to stronger mechanical shock. Furthermore it is advantageous if the coating material is dissolved under alkaline conditions, or is readily emulsified by surfactants. This avoids the deposition of undissolved particles or lumps of coating material on the laundry load. This may be important when the coating material is completely insoluble (for example less than 1 g/l) in water.

410 As defined herein "substantially insoluble" means having a very low solubility in water. This should be understood to mean having a solubility in water at 25°C of less than 20 g/L, preferably less than 5 g/l, and more preferably less than 1 g/l. Water solubility is measured following the test protocol of ASTM E1148-87 entitled, "Standard Test Method for Measurements of Aqueous Solubility".

415 Suitable coating materials are fatty acids, adipic acid and C8-C13 dicarboxylic acids, fatty alcohols, diols, esters and ethers. Preferred fatty acids are those having a carbon chain length of from C12 to C22 and most preferably from

C18 to C22. Preferred dicarboxylic acids are adipic acid (C6), suberic acid (C8), azelaic acid (C9), sebacic acid (C10), undecanedioic acid (C11), dodecanedioic acid (C12) and tridecanedioic acid (C13). Preferred fatty alcohols are those having a carbon chain length of from C12 to C22 and most preferably from C14 to C18. Preferred diols are 1,2-octadecanediol and 1,2-hexadecanediol. Preferred esters are tristearin, tripalmitin, methylbehenate, ethylstearate. Preferred ethers are diethyleneglycol mono hexadecylether, diethyleneglycol mono octadecylether, diethyleneglycol mono tetradecylether, phenylether, ethyl naphtyl ether, 2 methoxynaphtalene, beta naphtyl methyl ether and glycerol mono octadecylether. Other preferred coating materials include dimethyl 2,2 propanol, 2 hexadecanol, 2 octadecanone, 2 hexadecanone, 2, 15 hexadecanedione and 2 hydroxybenzyl alcohol. The coating is a hydrophobic material having a melting point preferably of from 40 °C to 180 °C.

In the preferred embodiment, the coating can be applied in a number of ways. Two preferred coating methods are a) coating with a molten material and b) coating with a solution of the material. In a), the coating material is applied at a temperature above its melting point, and solidifies on the tablet. In b), the coating is applied as a solution, the solvent being dried to leave a coherent coating. The substantially insoluble material can be applied to the tablet by, for example, spraying or dipping. Normally when the molten material is sprayed on to the tablet, it will rapidly solidify to form a coherent coating. When tablets are dipped into the molten material and then removed, the rapid cooling again causes rapid solidification of the coating material. Clearly substantially insoluble materials having a melting point below 40 °C are not sufficiently solid at ambient temperatures and it has been found that materials having a melting point above about 180 °C are not practicable to use. Preferably, the materials melt in the range from 60 °C to 160 °C, more preferably from 70 °C to 120 °C.


By "melting point" is meant the temperature at which the material when heated slowly in, for example, a capillary tube becomes a clear liquid. For most purposes, the coating forms from 1% to 10%, preferably from 1.5% to 5%, of the tablet weight.

Addition of Flow Aids

450 In the preferred embodiment, the process further includes the step of adding a flow aid to the particulate detergent composition in a range of from about 0.1% to about 25% by weight of the particulate detergent composition.

As used herein, the term "flow aids" means any material capable of being deposited on to the surface of detergent particles so as to reduce the stickiness of the detergent particles and allow them to flow freely. Flow aids could include
 455 porous carrier particles selected from the group consisting of amorphous silicates, crystalline nonlayer silicates, layer silicates, calcium carbonates, calcium/sodium carbonate double salts, sodium carbonates, clays, zeolites, sodalites, alkali metal phosphates, macroporous zeolites, chitin microbeads, carboxyalkylcelluloses,
 460 carboxyalkylstarches, cyclodextrins, porous starches and mixtures thereof.

The preferred flow aids are zeolite A, zeolite X, zeolite Y, zeolite P, zeolite MAP and mixtures thereof. The term "zeolite" used herein refers to a crystalline aluminosilicate material. The structural formula of a zeolite is based on the crystal unit cell, the smallest unit of structure represented by



where n is the valence of the cation M, x is the number of water molecules per unit cell, m and y are the total number of tetrahedra per unit cell, and y/m is 1 to 100.

Most preferably, y/m is 1 to 5. The cation M can be Group IA and Group IIA elements, such as sodium, potassium, magnesium, and calcium.

470 In the preferred embodiment of the present invention, the flow aid is added in an amount in a range, desirably, from about 0.1% to about 25% by weight of the particulate detergent, more desirably from about 1% to about 15% by weight, preferably from about 1% to about 10% by weight, and most preferably in an amount of about 5% by weight. It is undesirable to add more than 25% by weight
 475 of the flow aid because too excessive a force would be needed to make the detergent particles to stick together and stay in a particulate form. Flow aid addition in an amount less than about 0.1% by weight is also undesirable because little or no reduction in the stickiness of the detergent particles would occur, which

upon compression into a particulate form would cause the resultant detergent
480 tablet to not disintegrate readily when placed in water in a washing machine.

In one embodiment, the flow aids have a perfume adsorbed on their surface before being deposited on the detergent particles. Preferably, the flow aids are zeolites preferably containing less than about 20% desorbable water, more preferably less than about 8% desorbable water, and most preferably less than
485 about 5% desorbable water. Such materials may be obtained by first activating/dehydrating by heating to about 150 to 350 C, optionally with reduced pressure (from about 0.001 to about 20 Torr). After activation, the perfume is slowly and thoroughly mixed with the activated zeolite and, optionally, heated to about 60°C for up to about 2 hours to accelerate absorption equilibrium within the
490 zeolite particles. The perfume/zeolite mixture is then cooled to room temperature and is in the form of a free-flowing powder. The term "perfume" is used to indicate any odoriferous material which is subsequently released into the aqueous bath and/or onto fabrics contacted therewith. The perfume will most often be liquid at ambient temperatures. A wide variety of chemicals are known for
495 perfume uses, including materials such as aldehydes, ketones and esters. More commonly, naturally occurring plant and animal oils and exudates comprising complex mixtures of various chemical components are known for use as perfumes. The perfumes herein can be relatively simple in their compositions or can comprise highly sophisticated complex mixtures of natural and synthetic chemical
500 components, all chosen to provide any desired odor. Typical perfumes can comprise, for example, woody/earthy bases containing exotic materials such as sandalwood, civet and patchouli oil. The perfumes can be of a light floral fragrance, e.g., rose extract, violet extract, and lilac. The perfumes can also be formulated to provide desirable fruity odors, e.g., lime, lemon, and orange. Any
505 chemically compatible material which exudes a pleasant or otherwise desirable odor can be used in the perfumed compositions herein. Perfumes also include pro-fragrances such as acetal pro-fragrances, ketal pro-fragrances, ester pro-fragrances (e.g., digeranyl succinate), hydrolyzable inorganic-organic pro-fragrances, and mixtures thereof. These pro-fragrances may release the perfume material as a

510 result of simple hydrolysis, or may be pH-change-triggered pro-fragrances (e.g., pH drop) or may be enzymatically releasable pro-fragrances.

In the preferred embodiment, the amount of perfume adsorbed on the carrier material, such as zeolite for example, is preferably in the range of about 0.1% to about 50% by weight, more preferably in the range of about 0.5% to about 25% by
515 weight, and most preferably in the range of about 1% to about 15% by weight of zeolite powder.

Compaction of particulate detergent to form non-particulate detergent product

In the preferred embodiment, the process still further includes the step of compacting the particulate detergent composition having the flow aid by applying
520 a pressure in an amount sufficient to form the water-dispersible non-particulate detergent product having a density of at least about 1000 g/l. It is desirable to form a detergent tablet that has a density of at least about 1000 g/l so that the tablet will sink in water. If the density of the detergent tablet is less than about 1000 g/l, the tablet will float when placed in the water in a washing machine and this will
525 detrimentally reduce the dissolution rate of the tablet in the water. It is desirable to apply at least that much pressure as is sufficient to compress the particulate detergent material to form a tablet having a density of at least about 1000 g/l. Too little a pressure will result in a compressed tablet with a density less than about 1000 g/l.

530

EXAMPLE A

Detergent tablets are formed which have a flow aid deposited on the detergent particles before such particles are compressed into a tablet form, according to the following composition:

535

Table A.1

<u>Ingredients</u>	<u>% by weight</u>
Detergent particles	95.00
Flow Aid (zeolite A)	5.00
<hr/>	
Total	100.00

540

The detergent particles have the following composition:

Table A.2

	<u>Particulate detergent Ingredients</u>	<u>% by weight</u>
545	C ₁₂₋₁₆ linear alkylbenzene sulfonate	8.80
	C ₁₄₋₁₅ alkyl sulfate/C ₁₄₋₁₅ alkyl ethoxy sulfate	8.31
	C ₁₂₋₁₃ alkyl ethoxylate	1.76
	polyacrylate (MW=4500)	2.40
	polyethylene glycol (MW=4000)	0.96
550	sodium sulfate	8.40
	aluminosilicate	21.28
	sodium carbonate	16.80
	protease enzyme	0.32
	sodium perborate monohydrate	2.08
555	lipase enzyme	0.17
	cellulase enzyme	0.08
	NOBS extrudate	4.80
	citric acid monohydrate	2.25
	sodium bicarbonate	2.75
560	sodium acetate	15.00
	free water	1.60
	other minor ingredients (perfume etc.)	2.24
<hr/>		
	Total	100.00

565

The detergent tablet formed is coated with a coating according to the following composition:

Table A.3

570	<u>Ingredient</u>	<u>% by weight</u>
	Detergent tablet having flow aid	91.10
	Coating:	
	dodecanedioc acid	8.00
575	carboxymethyl cellulose	0.90
<hr/>		
	Total	100.00

The flow aid (zeolite) is added to the particulate detergent composition and mixed by one of various methods, such as agitation for example, in order to
580 homogeneously mix the flow aid with the detergent composition.. Alternatively, the flow aid is sprayed on the surface of detergent particle.

The tablets are formed by compressing the tablet ingredients in a cylindrical die having a diameter of 55 mm using a laboratory press having a trade name Carver Model 3912, to form a tablet having a height of 20 mm. The formed tablets
585 were then coated with the protective coating by dipping the tablet into a molten bath of the coating for about 3 seconds. The molten coating bath is maintained at a temperature of about 145 degrees centigrade.

The term "NOBS extrudate" as used herein, is an acronym for the chemical sodium nonanoyloxybenzene sulfonate, commercially available from Eastman
590 Chemicals, Inc. The carboxymethyl cellulose used in the above example is commercially available from Metsa-Serla and sold under the trade name, Nymcel ZSB-16.

Test for determining dispersibility in water

The following method is used to measure the rate of dispersion (ROD) of a
595 detergent tablet expressed as percentage residue remaining after "t" minutes, where "t" is 3, 5 and 10 minutes. The equipment used includes a 5000 ml glass beaker, a stopwatch with alarm, an electrical stirrer with variable speed IKA RW 20 DZM or equivalent, a cage made of perforated metal gauze (diameter 52 mm, height 40 mm

having 16 apertures each of about 2.5 mm square) and a weigh scale with accuracy
600 of 0.1 grams.

The method includes the following steps: The beaker is filled with 4000 ml
(+/-50 ml) of distilled water at 20 °C (+/- 1 °C). The cage tester is mounted in the
electrical stirrer. A tablet with a known weight is placed in the cage and the cage is
connected to the stirrer. The cage is submerged in the water with the cage
605 suspended about half way down the beaker and the stirrer is started at a fixed speed
of 80 rpm. The stopwatch is started. The stirrer is stopped after 3 minutes. The
cage is lifted out of the water and the tablet residue remaining in the cage is
weighed. The % residue is calculated with the following equation:

$$610 \quad \% \text{ residue} = \frac{\text{Tablet weight after "t" minutes}}{\text{Initial tablet weight}} \times 100$$

The remaining tablet is placed back in the cage and the process is repeated for an
additional 2 and 5 minutes to give yield data for tablet dispersion after 3, 5 and 10
minutes.

615 As used herein, the term "dispersibility in water" is defined as a measure of
the % residue, as calculated above, after 3 minutes. In other words, for example, a
detergent tablet which has 5% by weight less residue than another detergent tablet
would be deemed to have 5% greater dispersibility in water.

It has been unexpected and surprisingly discovered that the non-particulate
620 detergent product, e.g., a detergent tablet, has at least about 5% greater dispersability
in water as compared to another non-particulate detergent product having a density
of at least about 1000 g/l but not formulated with a flow aid according to this
invention. It has also been unexpectedly found that the water-dispersible non-
particulate detergent product has at least about 10% greater dispersability in water as
625 compared to a non-particulate detergent product having a density of at least about
1000 g/l and having a flow aid in an amount less than about 1% by weight of the
particulate detergent composition.

It has also been discovered that the water-dispersible non-particulate
detergent product formed by the process of the present invention has at least about

630 25% greater dispersability in water as compared to a non-particulate detergent product having a density of at least about 1000 g/l and having a flow aid in an amount less than about 2% by weight of the particulate detergent composition.

In the preferred embodiment of the present invention, the flow aid is added in an amount of about 5% by weight of the particulate detergent composition. It has
635 been unexpectedly discovered that by doing so, the water-dispersible non-particulate detergent product of the present invention has at least about 50% greater dispersability in water as compared to another non-particulate detergent product having a density of at least about 1000 g/l and having the flow aid in an amount less than about 5% by weight of the particulate detergent composition.

640 In another embodiment of the present invention, a method of laundering fabric materials in a washing machine includes the steps of providing a flexible porous bag adapted for receiving a non-particulate detergent product, providing a non-particulate detergent product, placing the non-particulate detergent product within the flexible porous bag, and placing the flexible porous bag containing the
645 detergent product in the washing machine with the fabric materials to be washed.

The flexible porous bag is permeable to water and to the washing medium and is thus adapted for permitting entry of an aqueous washing medium through the bag, thereby dissolving the non-particulate detergent product placed therein, into the aqueous washing medium, and releasing a resultant wash solution from inside of the
650 bag to outside of the bag and into the aqueous wash medium during a wash cycle.

The flexible porous bag is made of a material capable of retaining the non-particulate detergent product without allowing it to pass through until the detergent product has dissolved in the washing medium. The bag is also made of a material capable of withstanding the temperatures of washing laundry in a washing machine.
655 The process of the invention may be applied not only to non-particulate detergents but also to any non-particulate product which is active during washing, such as, for example, bleaching agents, such as agents releasing chlorine or active oxygen (peroxygen compounds), bleaching catalysts, bleaching activators, bactericides, foam regulators, whiteners, agents preventing the re-deposition of soil, enzymes,

660 softeners, agents capable of removing grease stains or other constituents having no direct effect on the soiling but capable of taking part in the laundry washing process.

The flexible bag may be made from any material which offers a sufficient resistance to water, such as a woven or non-woven material produced from natural or synthetic fibers. For example, the bag is formed of pure cotton either in the form of
665 a fabric with a mesh opening of less than about 0.5 mm or in the form of a non-woven article with openings having a size in a range of from about 0.5 mm to about 0.8 mm.

Accordingly, having thus described the invention in detail, it will be obvious to those skilled in the art that various changes may be made without departing from
670 the scope of the invention and the invention is not to be considered limited to what is described in the specification.

WHAT IS CLAIMED IS:

1. A process for producing a water-dispersible non-particulate detergent product, characterized by the steps of:
 - (a) providing a particulate detergent composition;
 - (b) adding a flow aid to said particulate detergent composition in a range of from 0.1% to 25% by weight of said particulate detergent composition; and
 - (c) compacting said particulate detergent composition having said flow aid by applying a pressure in an amount sufficient to form said water-dispersible non-particulate detergent product having a density of at least 1000 g/l.
2. The process of claim 1 wherein said flow aid is added in an amount in a range of from 1% to 15% by weight of said particulate detergent composition.
3. The process of any of claims 1-2 wherein said water-dispersible non-particulate detergent product has at least 5% greater dispersability in water as compared to a non-particulate detergent product having a density of at least 1000 g/l but not having said flow aid.
4. The process of any of claims 1-3 wherein said water-dispersible non-particulate detergent product has at least 10% greater dispersability in water as compared to a non-particulate detergent product having a density of at least 1000 g/l and having said flow aid in an amount less than 1% by weight of said particulate detergent composition.
5. The process of any of claims 1-4 wherein said water-dispersible non-particulate detergent product has at least 25% greater dispersability in water as compared to a non-particulate detergent product having a density of at least 1000 g/l and having said flow aid in an amount less than 2% by weight of said particulate detergent composition.

6. The process of any of claims 1-5 wherein said flow aid is in the form of porous carrier particles.
7. The process of any of claims 1-6 wherein said porous carrier particles are selected from the group consisting of amorphous silicates, crystalline nonlayered silicates, layered silicates, calcium carbonates, calcium/sodium carbonate double salts, sodium carbonates, clays, zeolites, sodalites, alkali metal phosphates, macroporous zeolites, chitin microbeads, carboxyalkylcelluloses, carboxyalkylstarches, cyclodextrins, porous starches and mixtures thereof.
8. The process of any of claims 1-7 wherein the step of providing a particulate detergent composition includes providing said detergent composition having a bulk density no greater than 900 g/l.
9. The process of any of claims 1-8 wherein the step of providing a particulate detergent composition includes providing said detergent composition having a bulk density in the range of from 600 g/l to 850 g/l.
10. The process of any of claims 1-9 wherein said water-dispersible non-particulate detergent product has at least 10% greater dispersability in water as compared to a non-particulate detergent product having a density of at least 1000 g/l and formed from a particulate detergent composition having a bulk density no greater than 700 g/l, when said flow aid is added in an amount greater than 1% by weight of said particulate detergent composition and when said particulate detergent composition has a bulk density no greater than 700 g/l.
11. A method of laundering fabric materials in a washing machine, characterized by the steps of:
 - providing a flexible porous bag adapted for receiving a non-particulate detergent product;

providing a non-particulate detergent product;
placing said non-particulate detergent product within said flexible porous bag;
placing said flexible porous bag containing said detergent product in said washing machine with said fabric materials to be washed; and

said flexible porous bag being adapted for permitting entry of an aqueous washing medium through said bag, thereby dissolving said non-particulate detergent product placed therein, into said aqueous washing medium, and releasing a resultant wash solution from inside of said bag to outside of said bag into said aqueous wash medium during a wash cycle.

12. A water-dispersible non-particulate detergent product, characterized by:
a core formed by compacting a particulate detergent composition to a density of at least 1000 g/l, said particulate detergent composition having a bulk density in a range of from 600 g/l to 850 g/l, and said particulate detergent composition characterized by a flow aid in a range of from 0.1% to 25% by weight of said particulate detergent composition.

13. A process for producing a water-dispersible non-particulate detergent product, characterized by the steps of:

- (a) providing a particulate detergent composition, wherein said particulate detergent composition is a mixture of a spray dried detergent and an agglomeration detergent present in a weight ratio in a range of from 40:60 to 80:20, spray dried:agglomeration detergent, the final bulk density of said detergent composition being no greater than 900 g/l;
 - (b) adding a flow aid to said particulate detergent composition in a range of from 0.1% to 25% by weight of said particulate detergent composition;
- and

compacting said particulate detergent composition having said flow aid by applying a pressure in an amount sufficient to form said water-dispersible non-particulate detergent product having a density of at least 1000 g/l.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/IB 99/00710

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C11D17/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 40 10 533 A (HENKEL KGAA) 10 October 1991 (1991-10-10) column 11, line 10 - column 15, line 30; claims 1-3,14,22; examples ---	1-10,12
X	DE 34 17 820 A (HENKEL KGAA) 14 November 1985 (1985-11-14) page 8, line 10 - page 9, line 26; claims; example 1 ---	1-10,12
X	PATENT ABSTRACTS OF JAPAN vol. 018, no. 568 (C-1266), 31 October 1994 (1994-10-31) & JP 06 207199 A (KAO CORP), 26 July 1994 (1994-07-26) abstract --- -/--	1,7-10



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"S" document member of the same patent family

Date of the actual completion of the international search

13 July 1999

Date of mailing of the international search report

28/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Grittern, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 99/00710

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 576 234 A (UNILEVER PLC ;UNILEVER NV (NL)) 29 December 1993 (1993-12-29) claim 14 ---	11
A	GB 2 276 345 A (UNILEVER PLC) 28 September 1994 (1994-09-28) page 18, line 3 - page 19, line 20; example 1 ---	1-10
A	DATABASE WPI Section Ch, Week 9434 Derwent Publications Ltd., London, GB; Class D25, AN 94-276042 XP062108982 & JP 06 207199 A (KAO CORP), 26 July 1994 (1994-07-26) abstract -----	1-6,9, 10,12,13

INTERNATIONAL SEARCH REPORT

information on patent family members

In. tional Application No

PCT/IB 99/00710

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 4010533 A	10-10-1991	AT 107352 T	15-07-1994
		AT 107350 T	15-07-1994
		DE 59006160 D	21-07-1994
		DE 59101947 D	21-07-1994
		DK 486592 T	18-07-1994
		WO 9102047 A	21-02-1991
		WO 9115567 A	17-10-1991
		EP 0486592 A	27-05-1992
		EP 0523099 A	20-01-1993
		ES 2055441 T	16-08-1994
		ES 2055599 T	16-08-1994
		JP 5500076 T	14-01-1993
		US 5318733 A	07-06-1994
		US 5382377 A	17-01-1995
DE 3417820 A	14-11-1985	AT 36347 T	15-08-1988
		DE 3564286 A	15-09-1988
		EP 0170791 A	12-02-1986
		JP 60252699 A	13-12-1985
		US 4642197 A	10-02-1987
JP 06207199 A	26-07-1994	NONE	
EP 0576234 A	29-12-1993	NONE	
GB 2276345 A	28-09-1994	BR 9401262 A	22-11-1994
JP 6207199 A	26-07-1994	NONE	